

# Effect of Transition Metal on Luminescence Quenching of ZnS Nanoparticles

Saurabh Khandelwal

Centre for Converging Technologies  
University of Rajasthan,  
Jaipur, 302004, India.

Gautam Aashish Kumar

Centre for Converging Technologies  
University of Rajasthan,  
Jaipur, 302004, India.

Ravi Agarwal

Centre for Converging Technologies  
University of Rajasthan,  
Jaipur, 302004, India.

Narendra Kumar Agrawal

Department of Physics  
Malaviya National Institute of Technology,  
Jaipur, 302017, India.  
E-mail: research.nka@gmail.com

**Abstract** — Quantum confinement effect changes the electronic structure of the nanocrystal. The most striking observation due to this effect is blue shift which is attributed to smaller particle size. ZnS nanoparticles are synthesized by chemical route gives a strong UV-Vis property at 315nm. But when these nanoparticles are doped with different nanoparticles their UV-Vis property changes which is used in optical filter design. We synthesized ZnS nanoparticles by chemical route with doping of Ni and characterized by UV-Visible photospectrometer, AFM in concentration range of 0 to 10 wt%. Variation in UV-Vis characteristic is recorded and discussed in this paper for different concentration of dopant ranging from 0 to 5 wt% for optical filter preparation.

**Keywords**— ZnS nanoparticles, doping, quantum confinement, UV-Vis, quenching

## I. INTRODUCTION

Sulfide semiconductor materials in the nano dimensional range have attracted great attention recently, as it posses such important properties which us useful in light converting electrodes [1], optical filters [2] and quantum devices [3]. ZnS is an important semiconductor material with a wide bandgap of 3.54 eV for the cubic phase [4] and 3.68 eV for the hexagonal wurtzite phase [5] at room temperature. ZnS is an inorganic compound. Mainly occuring in the minerals sphalerite and wurtzite which are intrinsic, wide-band gap semiconductors. Applications for the ZnS materials could be given as : white pigment, detector of alpha-rays, luminescent, infrared optics, used as phosphor in several applications, including X-ray screens and cathode ray tubes[6].

Here, we have used transition metal material for confining the particles which can be said as Nickel [7]. Coatings, and high-performance magnetic recording materials, magnetic fluid nanoparticles, Microwave-absorption materials. applications of copper nanoparticles: EMI shielding, highly thermal conductive materials, [8]efficient catalyst for chemical reactions and for the synthesis of methanol and glycol, displays, and transmissive conductive thin film applications[9]. Nickel is electrically conductive and hence used for several applications: magnetic fluid and catalyst, propellant and sintering additive[10,11].

In this paper we have carried out detailed study to identify the effect of doping in the ZnS nanoparticles which results in quenching of the nanoparticles, decreased bandgap, increased particle size.

## II. EXPERIMENTAL

ZnS nanoparticles were synthesized using wet chemical route. For the synthesis, EDTA (0.1 M) solution prepared in 20 ml distilled water. Then 10 ml of Zinc acetate (0.5 M) and 10 ml of Sodium sulphide (0.5 M) solution was added in EDTA solution drop by drop with stirring at room temperature and pressure. Stir the solution for 2 hours which leads to formation and precipitation of ZnS nanoparticles[12,13,14]. The solution was washed properly 4-5 times with distill water, dried in incubator and crushed using mortar pestel to obtain ZnS nanoparticles. For the synthesis of Ni doped ZnS nanoparticles Nickel Chloride solution (0.01 M in 100 ml) added drop by drop in EDTA solution along with Zinc acetate and Sodium sulphide solution[15,16]. The color of the solution turns out to be milky white which makes us to conclude that the ZnS nanoparticles formed. UV-Vis spectrum of NPs was taken using UV-Vis spectrophotometer SHIMADZU 1800[17,18,19]. The Nanosurf AFM used for the study of the particle size formation[20,21,22].




Fig. 1 UV-Vis characterization & Tauc Relation graphs of Ni doped ZnS Nanoparticles ( Pure ZnS, 0.1% Ni doped, 0.5% Ni doped, & 1% Ni doped nanoparticles)




Fig. 2 UV-Vis characterization & Tauc Relation graphs of Ni doped ZnS Nanoparticles ( 2% Ni doped, 5% Ni doped, 8% Ni doped & 10% Ni doped ZnS nanoparticles )




Fig. 3 AFM 3D graphs, standard graphs & line graphs (inset) graphs of Ni doped ZnS Nanoparticles (A) Pure ZnS Nanoparticles, (B) 1% Ni doped ZnS Nanoparticles, (C) 5% Ni doped ZnS Nanoparticles & (D) 8% Ni doped ZnS Nanoparticles



Sample	Bandgap (eV)	Table 1. Variation in bandgap with increasing dopant amount
Pure ZnS	2.4eV	This table represents the variation observed in the bandgap based on the calculations done using Tauc Plot. The observed values can be depicted as the pure ZnS nanoparticle bandgap found to 2.4eV with decreasing bandgap while the amount of the doping increased. Upto to a certain amount of doping material, the bandgap shows lowering value but as the maximum amount of dopant material used i.e 10%, we found that the bandgap increased suddenly. Hence, we conclude based on these results that after certain amount of doping, bandgap start to increase.
0.1% Ni	1.44eV	
0.5% Ni	1.41eV	
1% Ni	1.4eV	
2% Ni	1.41eV	
5% Ni	1.21eV	
8% Ni	1.21eV	
10% Ni	1.74eV	

The peak value for the ZnS nanoparticles found to be around 315nm using UV-Vis spectrophotometer & average particles size were also found using the same technique while the average band gap for the nanoparticles so synthesized found using the Tauc relation (fig 1,2). The doping of the transition metal found to decrease the band gap, increase the particle size & the absorbance peak shifts to the longer wavelength i.e Red shifting occurs. The average particle size found to be in 20nm for the pure ZnS nanoparticles while 65 nm for the maximum amount of the dopant used i.e 10% doping of nickel from the optical spectroscopy, while as the concentration of the dopant material is increased, it is observed that the particle size tend to increase while the band gap tend to show lower values ranging from pure ZnS nanoparticle which is having the bandgap around 2.4eV to maximum doping done as 10% Ni dopant in ZnS nanoparticles is 1.7eV (refer Table 1, fig. 1,2).

The AFM tool was used for the characterization of the pure nanoparticles & also the doped ones which when analyzed the particle size found to be in increasing order by using the depth profiling in the standard graphs with the line graphs indicating the average particles size (refer fig 3).

## SUMMARY & CONCLUSION

The color change of the solution from colorless to milky white is a indication of the formation of the ZnS nanoparticles after which Nickel added as in various amounts, the visual observation was the color change of the so obtained milky white solution turns into bluish by which, we concluded that doping is successful. The further characterization was done using UV-Vis photospectrometer which gives us the absorbance peak value, using this data, change in bandgap & average particle size was found. The AFM was also used for supporting the results obtained using UV-Vis about the average particles size.

## ACKNOWLEDGEMENT

Authors wish to thanks and acknowledge to Centre for Converging Technologies, UOR Jaipur for providing facility of UV-Vis Spectrophotometer and AFM.

## REFERENCES

- [1] Y. Sanchuan, L. Xuesong, L. Jingqun, W. Dihua, L. Meihong and G. Congjie, Surface modification of thin-film composite polyamide reverse osmosis membranes with thermo-responsive polymer (TRP) for improved fouling resistance and cleaning efficiency, Separation and Purification Technol. 76, 283-291 (2011).
- [2] B. Bagra, P. Pimpliskar and N. K. Agrawal, Bio-Compatibility, Surface & Chemical characterization of glow discharge plasma modified ZnO Nanocomposite Polycarbonate, proceedings of 58th DAE- Solid State Physics Symposium, AIP proceedings, Patiala India, Dec. 17-21 (2013).
- [3] P. Pimpliskar, B. Bagra, A. Gautam, S. Khandelwal and N. K. Agrawal, An Innovative Approach for Efficient and Reusable Catalization for Synthesis of  $\alpha$ ,  $\beta$ -Unsaturated Compounds Using Polymer - NPs Composites as Catalyst, proceedings of 58th DAE- Solid State Physics Symposium, AIP proceedings, Patiala India, Dec. 17-21 (2013).
- [4] L. Zou, I. Vidalis, D. Steele, A. Michelmore, S.P. Low and J.Q. Verberk, Surface hydrophilic modification of RO membranes by plasma polymerization for low organic fouling; J. of Memb. Sci. 369, 420-428 (2011).
- [5] N. K. Agrawal, N. A. Kumar, M. Singh, Y.K.Vijay and K.C.Swami, Plasma Surface Modification of Nano Composite Polymer Membranes: An Innovative Approach for Synthesis of Nano-Bio Materials, proceedings of 58th DAE- Solid State Physics Symposium, AIP proceedings, Patiala India, Dec. 17-21 (2013).
- [6] L. Meihong, Y. Sanchuan, Q. Ming, P. Qiaoming and G. Congjie, Impact of manufacture technique on seawater desalination performance of thin-film composite polyamide-urethane reverse osmosis membranes and their spiral-wound elements, J. of Memb. Sci. 348, 268-276 (2008).
- [7] H. Kanematsu, H. Ikegai and M. Yoshitake, Patents for Antibacterial Metallic Coating and Its Future Trend in Japan. Research Inventory, Int. J. of Eng. and Sci. 3(6), 47-55 (2013).
- [8] A. Goyal, V. Sharma, A. Sharma, R. Agarwal, K. B. Sharma and S. L. Kothari, Synthesis, structural and optical study of CdS nanoparticles doped with different concentration of Cu, J. of Nano-and Electronic Physics 3 (1), 254-259 (2011).
- [9] H. Kanematsu, H. Ikegai, and M. Yoshitake, Antibacterial Tin-Silver Plating by the Combination of Multistage Plating and Heat Treatment, J. of Appl. Surface Finishing 3, 114-118 (2008).
- [10] P. Agarwal, R. Agarwal and N. K. Agrawal, Morphology and Crystallization of Size-Controlled Spherical Silver Nanoparticles Synthesized Using Coriandrum sativum: A Greener Approach, proceedings of 58th DAE- Solid State Physics Symposium, AIP proceedings, Patiala India, Dec. 17-21 (2013).
- [11] W. M. King, P. A. Cantor, L.W. Schoellenback and C. R. Cannon, High-retention reverse-osmosis desalination membranes from cellulose acetate, Membranes from Cellulose Derivatives, Interscience Publisher, New York (2001), P. 203-207.
- [12] N. K. Agrawal, R. Agarwal, Y. K. Vijay and K. C. Swami, Characterization of N<sub>2</sub> Plasma Treated Nano Composites Polymer Membranes, J. of Mat. Sci. Surf. Eng. 1 (1), 4-7 (2013).

- [13] P. Agarwal, A. Mehta, S. Kachhwaha and S. L.; Kothari, Green Synthesis of Silver Nanoparticles and Their Activity Against Mycobacterium tuberculosis, Adv. Sci. Eng. Med., 5(7), 709-714 (2013).
- [14] J.K. Beasley, The evaluation and selection of polymeric materials for reverse osmosis membranes, Desalination, Interscience Publisher, New York (1997), P. 181-189.
- [15] R. Agarwal, N. K. Agrawal and Ramvir Singh, Cicer arietinum Leaf Extract Mediated Synthesis of Silver Nanoparticles and Screening of Its Antimicrobial Activity, Adv. Sci. Eng. Med. 6 (2), 203-207 (2014).
- [16] N. K. Agrawal, K. Awasthi, Y. K. Vijay and K. C. Swami, Synthesis and characterization of plasma treated TiO<sub>2</sub> Nano composites polymer membranes, J. of Adv. Electrochemistry "in press".
- [17] K. Hyun and K. S. Soo, Plasma treatment of thin film composite reverse osmosis membrane, J. of Memb. Sci. 286, 193-201 (2009).
- [18] N. K. Agrawal, M Singh, Y. K. Vijay and K. C. Swami, Synthesis and Characterization of Colloidal TiO<sub>2</sub> Nanoparticles: Acquire Through Titanium Chloride Rich Solutions, Adv. Sci. Eng. Med. 6 (5), 595-602 (2014).
- [19] N. K. Agrawal, R. Agarwal, Y. K. Vijay and K. C. Swami, Surface Modification of Ag Nano Composites Polymer Membranes by Glow Discharge Plasma, J. of Mat. Sci. Surf. Eng. 1 (1), 23-27 (2013).
- [20] N. K. Agrawal, R. Agarwal, Y. K. Vijay and K. C. Swami, Plasma etching technology for Surface and Chemical Modifications of Aluminium and PMMA Nanocomposites, Adv. Sci. Eng. Med. 6 (6), xxx-xxx (2014).
- [21] N. K. Agrawal, R. Agarwal, Y. K. Vijay and K. C. Swami, Reactive Polymer Surfaces for Cell Colonization, J. of Mat. Sci. Sur. Eng. 1 (1), xx-xx (2013).

IJERT