

Experimental Study on Flexuous Concrete

M. Renuga Devi¹, M. Nilavarasan², S. Sneha³, Mr. S. Manikandan⁴, Ms. S. Amutha⁵

^{1,2,3} Student civil, ⁴ Professor, ⁵ Assistant Professor

Sri Muthukumar Institute of Technology,
Chennai, India

Abstract- Engineered cementitious composites (ECC) also called as Flexuous concrete is an easily moulded mortar based composite specially selected short random fibres. Traditional concrete suffers catastrophic failure when strained in an earthquake or by routine overuse. ECC remains intact and safe to use at tensile strains up to 5%. Traditional concrete fractures and may not carry a load at 0.01 % tensile strain. In this paper, to overcome the demand for concrete in future and to develop the fibre materials, the Poly Vinyl Alcohol Fibre is used so as to reduce the cement content and to enhance flexibility. It has high aspect ratio, high ultimate tensile strength, relatively high modulus of elasticity, good chemical compatibility with Portland cement, good affinity with water and no health risks. To increase the workability of concrete super plasticizer is used. The compressive strength and flexural strength of cubes and slabs (two different thicknesses) is determined and also the bend ability characteristics of the concrete are checked during flexural strength test.

Keywords: ECC (Engineered Cementitious Composites) or Flexuous concrete, Poly Vinyl Alcohol fibre,(PVA) Super plasticizer.

INTRODUCTION

POLY VINYL ALCOHOL FIBER (PVA)

While selecting fibres for ECC, it was found that polyvinyl alcohol (PVA) fibre was of low cost and high performance. The hydrophilic nature of PVA fibre imposed great challenge in the composite design, as the fibres are susceptible to rupture instead of being pulled out because of the tendency for the fibre to bond strongly to cementitious matrix. The objective of this paper is to provide a performance summary of an exemplary PVA-ECC. PVA fibres have some structural strength and can also be used for shrinkage control. While they cannot replace reinforcing steel, they improve the mechanical properties of cured concrete, boosting its strength. Polyvinyl alcohol fibre (PVA) is an ideal environment-friendly cement reinforced material, which possesses alkali and weather resistance due to its unique molecular structure, taking on good affinity to cement, effectively prevent and suppress the crack formation and development, improve bending strength, impact strength and crack strength, improve permeability, impact and seismic resistance of concrete. This product can be widely used in civil and industrial buildings, walls, roofing, flooring and roads, bridges, tunnels, reinforcement for embankment slopes.

FLEXUOUS CONCRETE

Flexuous concrete also known as Engineered

Cementitious Composites abbreviated as ECC is class of ultra-ductile fibre cementitious composites, characterized by high ductility and tight crack width control.

Conventional concretes are almost unflexuous and have a strain capacity of only 0.1% making them highly brittle and rigid. This lack of bendability is a major cause of failure under strain and has been a pushing factor in the development of an elegant material namely, flexuous concrete. This material is capable to exhibit considerably enhanced flexibility. A flexuous concrete is micromechanically designed polymer fibres. ECC is made from the same basic ingredients as conventional concrete but with the addition of High-Range Water Reducing (HRWR) agent is required to impart good workability.

However, coarse aggregates are not used in ECCs, the powder content of ECC is relatively high. Cementitious materials, such as fly ash, silica fume, etc., may be used in addition to cement to increase the paste content. Additionally, ECC uses

low amounts, typically 2% by volume, of short, discontinuous fibres. ECC incorporates super fine silica sand and tiny Polyvinyl Alcohol-fibres covered with a very thin (manometer thick), silk coating. This surface coating allows the fibre to slipping when they are over loaded so they are not fracturing. It prevents the fibre from rupturing which would lead to large cracking. Thus an ECC deforms much more than a normal concrete but without fracturing. The behaviour of ECC under flexural loading and it can be seen that the beam can deform sufficiently without direct failure. ECC has proved to be 50 % more flexible than traditional concrete, and 40% lighter, which could even influence design choices in skyscrapers. Additionally, the excellent energy absorbing properties of ECC make it especially suitable for critical elements in seismic zones. The challenge in making a lightweight concrete is decreasing the density while maintaining strength and without adversely affecting cost. Introducing new aggregates into the mix design is a common way to lower density of concrete. Normal concrete contains four components, cement, crushed stone, river sand and water. The crushed stone and sand are the components that are usually replaced with lightweight aggregates.

I. INGREDIENTS OF ECC CONCRETE

Engineered cementitious composite is composed of

- Cement (53 grade of OPC)
- Sand
- Water

- Super plasticizer
- PVA fibre (length is 12mm and diameter is 40µm).

In the mix, coarse aggregates are deliberately not used because property of ECC Concrete is formation of micro cracks with large deflection. Coarse aggregates increases crack width which contradicts the property of ECC Concrete.

II. PROCEDURE FOR MAKING ECC CONCRETE MIX RATIO

The initial mix proportion was PVA fibre at 2% and super plasticizer dose was 30ml per slab mould (600x200x60 mm),(600x2000x30 mm) and 10ml per cube mould(70.6x70.6x70.6 mm), then water to cement ratio of 0.5. By using this proportion workability was achieved. The ratio of concrete mix is 1:2(cement : sand) and w/c=0.5.

Figure 1, 1.1, 1.2 shows the mixing of ECC concrete.

CASTING PROCEDURE OF ECC- CONCRETE.

The performance of the ECC Concrete was influenced by the mixing. This means that a proper & good practice of mixing can lead to better performance & quality of the ECC Concrete. The quality of the concrete is also influenced by the homogeneity of the mix material. Flexural Test was mix design was finalized, the mixing was carried out. The mixing of ECC Concrete was carried out by using hand mixing



Fig.1. Mixing of ECC concrete.



Fig.1.1 PVA Fibre



Fig.1.2. Mixture of ECC concrete.

The procedure of hand mixing was as follows:- Add sand, cement, add the PVA fibres slowly then add 50% of water & super plasticizer. Add slowly remaining quantity of water & super plasticizer and mix till the homogenous mixture is formed. Figure 2 and 2.1 represents the casting of cubes and slabs

PLACING, COMPACTING & CASTING OF CONCRETE SPECIMEN.

Before placing of concrete, the concrete mould must be oiled for the ease of concrete specimens stripping. Once the workability test of ECC concrete was done, the fresh concrete must be placed into the .



Fig.2. Casting of ECC concrete in cube.



Fig.2.1 casting of ECC concrete in slab

TESTING ON CONCRETE

After curing process, the specimen has to be tested. Investigations are carried out by testing cubes, slabs for 7, 14 days only the curing process for 28 days still not completed. Cubes were tested on Compression testing equipment and slabs of (two different thickness) were

tested on flexural testing machine and during this flexural testing the flexuous characteristics of slab also been Moulds for hardened property test . During the placing of fresh concrete into the moulds, tamping was done using Tamping rod in order to reduce the honeycombing. It allows full compaction of the fresh concrete to release any entrained air voids contained in the concrete. If the concrete was not compacted in a proper manner, the maximum strength of the concrete cannot be achieved. After this operation, the levelling of concrete was done on the surface of the concrete. Leveling is the initial operation carried out after the concrete has been placed & compacted. After the leveling of the fresh concrete was done, the concrete in the mould was left over night to allow the fresh concrete to set.



Figure 3 curing of concrete slab.

CURING OF CONCRETE SPECIMEN

After 24 hours, the concrete specimens are demoulded from the moulds. All the moulds are taken out from the specimen and the specimens were placed into the curing tank with a controlled temperature of 25 °C for a period of 28 days to attain the hardening property of concrete shown in figure 4 and 4.1 . Curing is an important process to prevent the concrete specimens from losing of moisture while it is gaining its required strength. Lack of curing will lead to improper gain in the strength. After 7 and 14 days of curing, the concrete specimens were removed from the curing tank to conduct hardened properties test of ECC Concrete. Fig.4. Curing of slabs.

Mechanical Properties

Mechanical	flexuous concrete	Conventional concrete
Compressive strength in N/mm² at		
7 days	27.5	25.5
14 days	36.8	35.3
Flexural strength in N/mm² at		
7 days	4.54	2.30
14 days	3.20	3.89
Flexural strength in N/mm² at		
7 days	3.40	3.20
14 days	5.20	4.30

determined for 7 days and 14 days respectively. The results are given in Table.1.

DISCUSSION

In the above comparisons the compression strength and flexural strength of the flexuous concrete is comparatively higher than the conventional cubes and slabs. The reason behind the higher strengths of flexuous concrete is due to the presence of fiber as reinforcement. The strength of conventional cubes and slabs is comparatively low since it is not reinforced. The 28 days strength of concrete is need to be checked

V. CONCLUSION

In this paper the compression and flexural strength of flexuous concrete is done and the values are compared with conventional cubes and slabs. Therefore it is proved that the flexuous concrete is having flexible and morflexural strength than the conventional concrete in 7 and 14 days and it is more flexible so that it resists crushing and cracking

REFERENCES

- [1] Vaipul solanki ,khadeeja priyam, Dr.Jayaesh kumar pitroda A Review on bendable concrete june 2021 About the characteristics of RCC and its properties
- [2] Sagar Gadhiya, Patel T N and Dinesh Shah(2015) "Parametric study on flexural strength on ECC 2015 ijscer vol:4 no:5
- [3] S.Z. Qian, J. Zhou, E. Schlangen "Influence of curing condition and pre cracking time on the self healing behaviour of Engineered Cementitious Composites" Journal of Cement & Concrete Composites 32 (2010) pp. 686–693.
- [4] Jian Zhou, Shunzhi Qian, Guang Ye, Oguzhan Copuroglu, Klaas van Breugel , Victor C. Li," Improved fibre distribution and mechanical properties of engineered cementitious composites by adjusting the mixing sequence," Journal of Cement & Concrete Composites" 34(2012)pp.342–348.
- [5] Seminar report on "Flexuous concrete "presented by Chitari Nagesh Babasahebi m.tech. in structural engineering Basaveshwar Engineering College Bagalkotacks and acts more efficient seismic regions
- [6] C.Neelagandan P. Santhosh EXP study and investigation on ecc using admixture 2016 the project was deals with exp study of ecc using admixture and adv and dis -adv of flexuous concrete
- [7] Balaji .R Exp study on flexuous concrete 2017 conventional concrete VS flexuous concrete
- [8] Vipul solanki ,Dr .k. priyan Review on flexuous concrete 2018 The additional strength of the fiber in the concrete load bearing structure
- [9] Dr R. Rajesh case study on flexuous concrete 2020 Application of ECC in load bearing structure
- [10] K.Selvakumar, R.Selva kumar Exp study on v flexuous concrete 2020 About ecc comparison on Traditional and flexuous concrete
- [11] P. Sathish Investigation study on ECC concrete 2021 comparison and application on ECC in structures.
- [12] Sagar Gandhiya, Patel TN and Dinesh Shah(2015) "Parametric study on flexural strength on ECC 2015 I jscer vol:4 no:5
- [13] Michael D. Lepech a, Victor C. Li, (2009), "Water permeability of Engineered Cementitious
- [14] Michael D. Lepech, Victor C. Li, Richard . Robertson, and Gregory A. Keoleian (2008) "Design of Green Engineered Cementitious Composites for Improved Sustainability" ACI Materials Journals, V.105, No.6, pp-567-575.

- [15] Victor C. lia, H. Horiib, P. Kabeleb, Y.M. Lim“Repair and retort with engineered cementitious composites”, Engineering Fracture V65, pp317-334.
- [16] Yingzi Yang I, Michael D. Lepech, En-Hua Yang, Victor C. Li, (2009)“Autogenoushealingof engineered cementitious composite under wet- drycycles”, Cement and Concrete Research, V -39, pp 382-390.IS 12269:1987-Specification for 53 grade ordinary Portland cement.IS 456:2000-Plain and reinforced concrete-Code of practice. Concrete-Code of practice.IS 383 – 1970, the fine aggregate belongs to zone.IS: 516-1959 “Method of Test for strength of concrete”,Bureau of Indian Standards,New Delhi.